



Fawori Silicone Texture Exterior Paint

PRODUCT DESCRIPTION

Acrylic copolymer emulsion-based, silicone-added, roller-applied and coral roller-patterned, matte, top-coat, grained exterior coating.

SPECIFICATIONS

- ✓ Contains silicone
- ✓ Matte
- ✓ Water repellent
- ✓ High covering power
- ✓ Breathable
- ✓ Textured
- ✓ 5-year UV-resistance guarantee

High adherence quality. Holds on to the application surface well thanks to its high adherence power. Resistant to atmosphere conditions, pollution, UV rays and friction. Easy application as it quickly spreads over the surface. Water resistant thanks to its water repellent quality.

APPLICATION SURFACES

Can be applied to plaster, concrete, brute concrete, concrete board, MDF, OSB, and even to old painted surfaces that can still support themselves even though they may have lost their color.

APPLICATION

Ensure that the application surface is solid, dry, clean, and self-supporting. On concrete, exposed concrete and new plastered surfaces, the setting time should be observed (28 days). Correct and repair the surface if required. Cover especially the exposed concrete surfaces with the suitable paste and primer in case they are porous. Prime with Fawori Exterior Silicone Primer before covering. Can be applied to the surface using any roller or spraying method without thinning. Pattern the top coat by combing with crystal pored coral roller downwards. Since combing in multiple directions will cause pattern differences, it would not be possible to solve this problem by painting. Ensure that the ambient and the surface temperatures are between +5 °C and +30 °C during application and until the end of drying time, and protect the surface from all kinds of precipitation, dew and frost. Avoid application in windy days. Not recommended to be applied from 10:00 AM to 04:00 PM on weather conditions over 25°C. Recommended to be applied to shady walls. The required conditions must be met to obtain the standard pattern and to prevent sudden water loss of the material.

Our products should be applied on substructure surfaces that are built in line with 30.06.2007 dated General Construction Specifications No. 26568.



WARNINGS

For cement-based surfaces that will be painted for the first time, mix Fawori Exterior Paste with fresh white/gray cement and a water mixture that is equal to 20% of its weight. Apply the mixture directly on cleaned and moisturized plaster/concrete surfaces. If a plaster application will be applied on old painted surfaces, heavy scoring must be applied to reach the raw plastered surface. Ensure that the ready-to-use pastes are applied with maximum 1 mm of thickness in order to prevent cracking and slumping.

Apply Stako 0 for a 0-3 mm surface for leveling and correcting. Recommended to use 1 kg of Latex + 4 kg of water for thinning.

Apply Stako for a 3-10 mm surface for leveling and correcting. Recommended to use 1 kg of Latex + 4 kg of water for thinning.

Apply Stako Plus for a 5-40 mm surface for leveling and correcting. Recommended to use 1 kg of Latex + 4 kg of water for thinning.

Apply glass-fiber mesh with 10 cm width along the crack if the crack continues as a straight line and with 10 cm at all joints throughout the surface if there are numerous cracks. Ensure the glass-fiber mesh is applied as close to the exterior surface as 1/3 of the total thickness of the surface correction and leveling material.

Protect the surfaces from extreme dew and rain especially during the period from the cement-based surface correction / repair paste application to the final coat application. Otherwise, there will be efflorescence. In such a case, moisten the surface with a car wash brush and apply 1 unit of Disboxan 451 + 1 unit of water mixture.

For airless spraying:

Pressure : 200 bar
Nozzle Angle: 50°C
Nozzle Size (inch): 0.047"
Thinning: Ready to use. Never thin.

THINNING

Ready to use Never thin.

DRYING TIME (@ 20°C, 65% RH):

| | |
|-------------------------------------------|---------------|
| Touch dry: | 30-45 minutes |
| Drying period between primer and coating: | 6-8 hours |
| Final drying: | 24 hours |

CONSUMPTION

Depending on the type, absorbency, structure and desired pattern of the surface to be applied, an area of 0.8-1.3 m² can be covered with 1 Kg. Perform a controlled sample run to estimate the precise consumption amount.

STORAGE

It can be stored in its unopened package for 3 years, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application.

PACKAGE

25 kg

WARNING STATEMENT

Caution

HAZARD STATEMENT



H317 May cause an allergic skin reaction.

PRECAUTIONARY STATEMENTS

P101 If medical advice is needed, have the product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P261 Avoid breathing dust/fume/gas/mist/vapors/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P333+P313: If skin irritation or a rash occurs: Get medical advice/attention. P501

Dispose of contents/container in accordance with local, regional, national and international regulations.

In compliance with TS 7847.

G
TSI

Complies with the G communiqué.

Patterned plaster that is applied and patterned with a roller

| | |
|----------------------------------------|---|
| Silicone Rough Exterior Facade Coating | 1 |
| PRODUCT DESCRIPTION | 1 |
| SPECIFICATIONS | 1 |
| APPLICATION SURFACES | 1 |
| APPLICATION | 1 |
| | 2 |
| WARNINGS | 2 |
| For airless spraying: | 2 |
| THINNING | 2 |
| DRYING TIME (@ 20°C, 65% RH): | 2 |
| CONSUMPTION | 2 |
| STORAGE | 2 |
| PACKAGE | 2 |
| WARNING STATEMENT | 2 |
| HAZARD STATEMENT | 3 |

| | |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---|
| | 3 |
| PRECAUTIONARY STATEMENTS | 3 |
| In compliance with TS 7847. | 3 |
| Complies with the G communiqué. | 3 |
| Pos. No. | 4 |
| This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001. | 4 |
| Rev3 March 2020 | 4 |

Pos. No.
25,034/2

Rate No 04.522/D

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

Rev3 March 2020